

## easy-on test information

Abrasion Resistance	135.3mg/1000 cycles (Emulsion = 558.7mg/1000 cycles)
Adhesion	<17.4 mPa at 2600 psi.
Asbestos Encapsulation	Ruder Boskovitch Institute test - pass
ASTM D6578-00	Standard for determination of graffiti resistance
Bacteria Resistance	100% removal of Hospital Acquired Infections (HAI's)
Biomedical Research Centre	97.73% reduction on easy-on+
Brake Fluid Resistance	24 hour contact - no change
Chemical resistance	8 chemicals tested
Contact Angle	89° - Hydrophobic
Ease of Decontamination (EOD)	BS 4247 part 1 - rated excellent
Food Contact	US Dept of Agriculture MPI-2
Fire Test Results	easy-guard / easy-on fire test results
GRP Panels Fire test	BS 6853:1999 Annex D.8.4 (Panel Test) WF 166017
IFTA AG Zertifiziertes	easy-on+ anti bacterial test.
Irradiation Test	1.25 MeV Gamma, Harwell- IEC-60544 part 2
London Underground Ltd	easy-on registration 1178
London Underground Ltd	easy-off registration 1177
London Underground Ltd	Standard 2-01001-002
Permanency Test	Material Research Institute photographs
Spread of Flame	BRE results BS476 parts 6 & 7 1989
Steam Pressure resistance	4000 psi @
SYPOL	easy-on certification
SYPOL	easy-off certification
Transfire Services Ltd	London Underground Engineering Standard E1042 A6
UV Resistance	Virtually unaffected by UV
Vapour Transmission	40 grammes / square metre / 24 hours @ 30 micron dft
VITO Technologist, Belgium	Graffiti removal test
Warrington Fire Blue Board	Class 4 blue board list to Class '1' and Class '0'
Warringtonfire	easy-guard/easy-on BS 476 Part 6:1989 and part 7:1997